

		SCHEDA ARTICOLO				N° PSQ 008/06 Edizione 01 Rev.03 Data em. 20/05/2010	
Data : 22/02/2024		R.C.	100	Articolo: <u>TEMPOTEST HOME tailor made</u> Disegno: <u>51973</u>			Scheda nr. 639
CARATTERISTICA VALUTATA CHARACTERISTICS HAUPTMERKMALE CARACTERISTIQUES		UNITA' DI MISURA UNIT MASSEINHEIT UNITÉ		RISULTATI OTTENUTI SUI CAMPIONI RESULT ERGEBNISSE RESULTAT			NORME
Altezza pezza / Width Stückbreite/Hauteur pièce		cm		145 (+/-3)			
Peso tessuto / Weight Gewicht/ Poids tissu		gr/m ²		290 (+/-5%)			
Armatura/Weave Gewebebindung/Armure				TELA			
Composizione / Composition Zusammensetzung / Composition		%		100% FILATO ACRILICO PER OUTDOOR			
Carico alla rottura / Breaking load Reißfestigkeit / Charge de rupture		N		Ordito/Warp /Kette/Chaîne	1400	Trama/Weft Schuß/Trame	600 UNI EN ISO 13934 – 1
Allungamento a rottura / Extensibility Höchstzugkraftdehnung /Allongement à rupture		%		Ordito/Warp /Kette/Chaîne	41,5	Trama/Weft Schuß/Trame	17,5 UNI EN ISO 13934 – 1
Tenuta alla cucitura / Sewing (resistance) / Nahtwiderstand / Resistance à la couture		mm		Ordito/Warp /Kette/Chaîne	180 N 6	Trama/Weft Schuß/Trame 2	UNI EN ISO 13936-2
Martindale		N°cicli/N°cycles Touren/N°cycles		22.000			UNI EN ISO 12947-2
Pilling al martindale		N° cicli / N° cycles Touren / N° cycles		Valore Medio 4 A 2. 000 cicli			UNI EN ISO 12945 - 2
Solidità dei colori alle intemperie artificiali prova con lampada ad arco allo xeno: Colour fastness to artificial weathering Xenon are fading lamp test: Lichtechtheit der Farben bei künstlicher Bewitterung. Test durch Xenonbogenlicht: Solidité coloris aux intempéries artificielles:				grado 4/5-5 dopo 1000 ore di esposizione scala dei grigi degree 4/5-5 after 1000 hour of exposure on the grey scale Stufe 4/5-5 Grauskala nach 1000 Stunden Belichtung degré 4/5-5 sur l'échelle des gris après 1000 heures d'exposition			UNI EN ISO 105 – B04
Finissaggio: Finishing: Ausrüstung: Finissage:		Idrorepellente con trattamento PFAS free Water-repellent with PFAS freefinishing, Wasserbstossend, mit PFAS free Ausrüstung. Repoussant à l'eau avec finissage PFAS free					
    							